

Chem-Impex International, Inc.

Tel: (630) 766-2112

E-mail: sales@chemimpex.com

Shipping and Correspondence:

935 Dillon Drive

Wood Dale, IL 60191

Fax: (630) 766-2218

Web site: www.chemimpex.com

Manufacturing site:

825 Dillon Drive

Wood Dale, IL 60191

Product Specifications

Catalogue Number 38751

Product

Kolliphor P 188

Poloxamer 188

Poly(ethylene glycol)-block-poly(propylene glycol)-block-poly(ethylene glycol)

Appearance White prill/cast solid

Color (APHA) ≤ 100 (50:50 in MeOH)

Solubility Colorless solution

Solubility (Turbidity) Clear solution (100 mg/mL in water)

Melting Point 53 - 56 °C

Viscosity 700 - 1300 cps at 77 °C

Water Content (Karl Fisher) $\leq 0.75\%$

pH 5 - 8 (2.5% solution)

Storage Store at RT

Additional Information Cloud point : ≥ 100 °C (10% solution)

For Laboratory Use Only